

	FABRIC TYPE	MESH COUNT		MESH OPENING	OPEN AREA	FABRIC THICKNESS	THEORETICAL INK VOLUME	MAXIMUM RECOMMENDED TENSION	
		cm	inch	μ	%	μ	cm³/m²	N/cm	
+	6TT	29	74	234	46	142	65	25	
	8TT	34	86	184	39	150	58	25	
+	10TT	43	110	135	33	114	38	25	
	12TT	48	122	118	25	113	28	₊ 23	_
	14TT	48	122	98	24	112	27	23	
+	14TT/SP	55	140	105	33	105	35	23	
	16TT	62	158	80	24	105	24	21	
	18TT +	66	168	91 ⁺	36	+85	+ 31	+ 21	-
	20TT	69	175	87	34	85	29	21	
	25TT	77	196	69	28	83	24	21	

The above data are average values measured on piece-good in relaxed state, manufactured with yarns of a perfect nominal diameter (cfr. international standards), under normal hygrometric conditions (20°=68°F, 65% relative umidity). They are subject to normal variations up to 7% if conditions vary from those stated above.

